

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
17 August 2006 (17.08.2006)

PCT

(10) International Publication Number
WO 2006/084912 A1

(51) International Patent Classification:

A61L 27/54 (2006.01) A61L 27/34 (2006.01)
A61L 29/16 (2006.01) A61L 29/08 (2006.01)
A61K 31/74 (2006.01) A61L 31/10 (2006.01)
A61K 31/785 (2006.01) A61L 31/16 (2006.01)

(21) International Application Number:

PCT/EP2006/050891

(22) International Filing Date:

13 February 2006 (13.02.2006)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

05002935.4	11 February 2005 (11.02.2005)	EP
60/652,760	14 February 2005 (14.02.2005)	US
05018269.0	23 August 2005 (23.08.2005)	EP
60/711,006	24 August 2005 (24.08.2005)	US

(71) Applicant (for all designated States except US): NOLabs
AB [SE/SE]; Kungsgatan 6, S-252 21 Helsingborg (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): PETERS, Tor
[SE/CH]; Chalet Marabou Bodemos, CH-1659 Rouge-
mont (CH).


(74) Agent: KRAHBICHLER, Erik; Ström & Gulliksson AB,
Järnvägsgatan 3, S-252 24 Helsingborg (SE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,
LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI,
NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG,
SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

[Continued on next page]

(54) Title: DEVICE METHOD, AND USE FOR TREATMENT OF NEUROPATHY INVOLVING NITRIC OXIDE



(57) Abstract: A device and method for therapeutical treatment of disorders in the oral cavity and a process for manufacturing of said device is disclosed. The device comprises a nitric oxide (NO) eluting polymer. The nitric oxide (NO) eluting polymer is configured to elute a therapeutic dosage of nitric oxide (NO) when used in the oral cavity. The device allows for target treatment of infections or wounds in the oral cavity. The device comprising the nitric oxide (NO) eluting polymer is arranged to contact an infected area in the oral cavity, such that a therapeutic dose of nitric oxide is eluted from said nitric oxide eluting polymer to said area. The nitric oxide (NO) eluting polymer is integrated with a carrier material, such that said carrier material, in use, regulates and controls the elution of said therapeutic dosage of nitric oxide (NO).



FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

— *before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments*

Published:

— *with international search report*

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

DEVICE METHOD, AND USE FOR TREATMENT OF NEUROPATHY INVOLVING NITRIC OXIDE**Field of the Invention**

5 This invention pertains in general to the field of treatment of neuropathy, such as diabetic peripheral neuropathy, vaso-constrictive disorders, macro-angiopathy and slow healing wounds as consequence of diabetic neuropathy and impaired blood circulation due to diabetic
10 disease or obstructed blood flow caused by other disease. More particularly the invention relates to a device for treatment of at least some of said disorders, and a process for manufacturing of said device, involving the use of nitric oxide (NO).

15

Background of the Invention

 Diabetes is a disorder that affects millions of people around the world. This disease results in increased risk for neuropathy and macro-angiopathy. Reasons for
20 diabetic neuropathy may be varying levels of insulin or blood sugar respectively, and high blood sugar. Diabetic neuropathy, or nerve damage, resulting from chronically high blood sugars, can be one of the most frustrating and debilitating complications of diabetes, because of the
25 pain, discomfort and disability it can cause, and because available treatments are not uniformly successful.

 Diabetic neuropathy may be divided into the three main types of neuropathy; sensory neuropathy, autonomic neuropathy, and motor neuropathy. Sensory neuropathy leads
30 to pain, numbness, tingling in the extremities, and even the inability to feel heat, cold, pain or any other sensation in the affected areas. Autonomic neuropathy leads to impotence (in men), bladder neuropathy, diabetic diarrhea, or swollen stomach. Motor neuropathy leads to
35 muscle weakness.

 As a direct and indirect consequence of diabetic neuropathy the person suffering from this disorder may

develop ulcers, so-called diabetic ulcers. These diabetic ulcers may develop as a result of small traumas on the body. Since the diabetic person, suffering from diabetic neuropathy, has a reduced, and some times even non-
5 existent, ability to feel, these ulcers may develop very rapidly. Other factors that severely affect this matter are the reduced ability to heal and the reduced circulation in the affected area, which accompanies diabetic neuropathy. The reduced circulation in the affected area is a
10 consequence of macro-angiopathy. Macro-angiopathy is a condition in which the blood vessels are enlarged and the arteries are hardened. These ulcers often result in amputation of the affected extremity. Macro-angiopathy is closely related to Peripheral Artery Obstructive Disease,
15 and will therefore here on after be treated as the same.

Other malfunctions arising from diabetic neuropathy are vaso-constrictive disorders, such as Raynouds, or Reyes syndrome.

Up to this point in time, there are no good cures or
20 treatment of neuropathy. Some medications, such as acetaminophen, aspirin, ibuprofen, amitriptyline, desipramine, and capsaicin, are on the market to liberate the diabetic person from pain, but these medicaments do not deal with the malfunction itself, only with the symptoms,
25 and sometimes develop resistance against the active pharmaceutical substance in the medication. The person suffering from said disorders is instructed to apply these medicaments in form of creams and peroral compositions regularly during the day, rather than waiting for the pain
30 to become severe. This is an all day process, which is very frustrating for the person suffering from said disorders. It is believed, in some circumstances, that these creams and compositions block pain signals, although they do not work for everyone. Occasionally, these creams and
35 compositions may even worsen the pain or cause other

adverse effects, such as eye or skin irritation. In the late 1980s and early 1990s aldose reductase inhibitors were introduced. Unfortunately, to date none of these drugs has proven to be sufficiently effective and adverse side effects have been a concern. Instead, the best advice the person suffering from said disorder can get, is to control and regulate his/her way of living, such as keeping blood sugar levels as close to normal as possible, exercise regularly, and take care of their health and weight.

10 It is known that nitric oxide (NO) provides an alternative to conventional therapies, such as antibiotics. Nitric oxide is a highly reactive molecule that is involved in many cell functions. In fact, nitric oxide plays a crucial role in the immune system and is utilized as an effector molecule by macrophages to protect itself against a number of pathogens, such as fungi, viruses, bacteria etc., and general microbial invasion. This improvement of healing is partly caused by NO inhibiting the activation or aggregation of blood platelets, and also by NO causing a reduction of inflammatory processes at the site of an implant.

 NO is also known to have an anti-pathogenic, especially an anti-viral, effect, and furthermore NO has an anti-cancerous effect, as it is cytotoxic and cytostatic in therapeutic concentrations, i.e. it has among other effects tumoricidal and bacteriocidal effects. NO has for instance cytotoxic effects on human haematological malignant cells from patients with leukaemia or lymphoma, whereby NO may be used as a chemotherapeutic agent for treating such haematological disorders, even when the cells have become resistant to conventional anti-cancer drugs. This anti-pathogenic and anti-tumour effect of NO is taken advantage of by the present invention, without having adverse effects as for instance many anti-cancer drugs.

However, due to the short half-life of NO, it has hitherto been very hard to treat viral, bacteria, virus, fungi or yeast infections with NO. This is because NO is actually toxic in high concentrations and has negative effects when applied in too large amounts to the body. NO is actually also a vasodilator, and too large amounts of NO introduced into the body will cause a complete collapse of the circulatory system. On the other hand, NO has a very short half-life of fractions of a second up to a few seconds, once it is released. Hence, administration limitations due to short half-life and toxicity of NO have been limiting factors in the use of NO in the field of anti-pathogenic and anti-cancerous treatment so far.

In recent years research has been directed to polymers with the capability of releasing nitrogen oxide when getting in contact with water. Such polymers are for example polyalkyleneimines, such as L-PEI (Linear PolyEthyleneImine) and B-PEI (Branched PolyEthyleneImine), which polymers have the advantage of being biocompatible.

US 5,519,020 describes water insoluble polymeric NONOate complexes, such as PEI-C and S-nitroso-compounds, which are capable of accelerating wound repair through the controlled therapeutic release of NO. Clinical applications of the device according to US 5,519,020 include treatment of burns, burn donor sites, chronic venous ulcers, decubitus ulcers, leprous ulcers, epidermolysis bullosa, scleroderma, psoriasis, and non infected partial thickness wounds. However, the elution of nitric oxide from the polymer according to 5,519,020 is not regulated in any way. Furthermore, US 5,519,020 is totally silent about the treatment of neuropathy.

Bohl Masters KS; Leibovich S J, Belem P, West J L, Poole-Warren L A, "Effects of nitric oxide releasing poly(vinyl alcohol) hydrogel dressings on dermal wound healing in diabetic mice", Wound Repair Regeneration, vol.

10, no. 5, 2002, pages 286-294, XP002335426 US, describes in vitro and in vivo responses to a novel hydrogel, manufactured by ultraviolet light-initiated polymerization from poly(vinyl alcohol) with a NO donor covalently coupled to the polymer backbone, that produces therapeutic levels of NO. However, the elution is not regulated in any way. Furthermore, this document is totally silent about the treatment of neuropathy.

US 6,737,447 discloses a coating for medical devices, which coating provides NO delivery by using nanofibers of L-PEI. However, the elution of nitric oxide from the polymer according to US 6,737,447 is not regulated in any way. Furthermore, US 6,737,447 is totally silent about the treatment of neuropathy.

EP 1 300 424 discloses extremely hydrophobic NO releasing polymers. These polymers are extensively cross-linked polyamine-derivatized divinylbenzene diazeniumdiolates. However, the elution of nitric oxide from the polymer according to EP 1 300 424 is not regulated in any way. Furthermore, EP 1 300 424 is totally silent about the treatment of neuropathy.

US 2004/0171589 discloses local, differential delivery of nitric oxide within the body. US 2004/0171589 mentions that the device according to US 2004/0171589 may be used for placement on skin wounds or openings, page 2, left column, lines 5 to 6. Furthermore, US 2004/0171589 discloses polyethyleneimine microspheres, with an attached diazeniumdiolate moiety, for long in-situ half-life applications, page 6, right column, lines 1 to 5. However, the elution of nitric oxide from the polymer according to US 2004/0171589 is not regulated in any way. Furthermore, US 2004/0171589 is totally silent about the treatment of neuropathy.

Other example for NO eluting polymers are given in US-5,770,645, wherein polymers derivatized with at least

one -NO_x group per 1200 atomic mass unit of the polymer are disclosed, X being one or two. One example is an S-nitrosylated polymer and is prepared by reacting a polythiolated polymer with a nitrosylating agent under
5 conditions suitable for nitrosylating free thiol groups.

Akron University has developed NO-eluting L-PEI molecule that can be nano-spun onto the surface of permanently implanted medical devices such as implanted grafts, showing significant improvement of the healing
10 process and reduced inflammation when implanting such devices. According to US 6,737,447, a coating for medical devices provides nitric oxide delivery using nanofibers of linear poly(ethylenimine)-diazoniumdiolate. Linear poly(ethylenimine)diazoniumdiolate releases nitric oxide
15 (NO) in a controlled manner to tissues and organs to aid the healing process and to prevent injury to tissues at risk of injury.

However, the meaning of "controlled" in the context of US 6,737,447 is only directed to the fact that nitric
20 oxide is eluted from the coating during a period of time. Therefore, the interpretation of "controlled" in respect of US 6,737,447 is different from the meaning of "regulating" in the present invention. "Regulate", according to the present invention is intended to be interpreted as the
25 possibility to vary the elution of nitric oxide to thereby achieve different elution profiles.

Electrospun nano-fibers of linear poly(ethylenimine) diazoniumdiolate deliver therapeutic levels of NO to the tissues surrounding a medical device while minimizing the
30 alteration of the properties of the device. A nanofiber coating, because of the small size and large surface area per unit mass of the nanofibers, provides a much larger surface area per unit mass while minimizing changes in other properties of the device.

However, the disclosure is both silent concerning an improvement of present technology in respect of treatment of neuropathy, such as diabetic neuropathy, diabetic ulcers, vaso-constrictive disorders, and enlarged and
5 hardened blood vessels, and the anti pathogenic potential of nitric oxide.

Hence, an improved, or more advantageous, device for therapeutic treatment and/or prevention of neuropathy, such as diabetic neuropathy, diabetic ulcers, and macro-
10 angiopathy is needed. It is desired that said device does increase circulation in the affected area while affecting nerves positively, has a vaso-dilating effect, reduces pain and heals wounds, which device is easy to use, and cost effective, and which device does not develop resistance
15 against the active pharmaceutical substance, and which does not cause local skin or eye irritation, pain etc, would be advantageous, and in particular a device allowing for target prevention and treatment of neuropathy, such as diabetic neuropathy, diabetic ulcers, and enlarged and
20 hardened blood vessels, would be advantageous.

Summary of the Invention

Accordingly, the present invention preferably seeks to mitigate, alleviate or eliminate one or more of the
25 above-identified deficiencies in the art and disadvantages singly or in any combination and solves, among others, the problems mentioned above, by providing a device according to the appended patent claims.

According to one aspect of the invention, a device is
30 provided that allows for target treatment and/or prevention of neuropathy, such as diabetic neuropathy, diabetic ulcers, vaso-constrictive disorders and macro-angiopathy. The device comprises a nitric oxide (NO) eluting polymer arranged to contact the affected area, such that a

therapeutic dose of nitric oxide is eluted from said nitric oxide eluting polymer to said area.

According to another aspect of the invention, a manufacturing process for such a device is provided, wherein the process is a process for forming a device that allows for target treatment and/or prevention of neuropathy, such as diabetic neuropathy, diabetic ulcers, and macro-angiopathy. The process comprises selecting a plurality of nitric oxide eluting polymeric fibers, and
10 deploying said nitric oxide eluting fibers in a condom/sheath, patch/dressing or tape/coating to be comprised in said device.

According to still another aspect of the present invention, a use of nitric oxide in a medicament to treat
15 or prevent neuropathy is provided.

The present invention has at least the advantage over the prior art that it provides target exposure of an affected area to NO, whereby an increased circulation in the affected area, a vaso-dilating effect, a positive
20 effect on nerves, pain reduction and wound healing, while not developing resistance against the active pharmaceutical substance, local skin or eye irritation, pain etc, are simultaneously obtained.

25 **Brief Description of the Drawings**

These and other aspects, features and advantages of which the invention is capable of will be apparent and elucidated from the following description of embodiments of the present invention, reference being made to the
30 accompanying drawings, in which

Fig. 1A is a schematic illustration of a treatment device embodiment 10,

Fig. 1B is a schematic illustration of a sock 12 according to an embodiment of the invention,

Fig. 2 is a schematic illustration of a tape or coating 20 according to another embodiment of the invention,

Fig. 3 is a schematic illustration of a sheath or plaster 30 according to a further embodiment of the invention, and

Fig. 4 is a graph illustrating different elutions of nitric oxide from two polymer mixtures.

10 **Description of Embodiments**

The following description focuses on embodiments of the present invention applicable to a device, which allows for simultaneous target treatment and/or prevention of neuropathy, such as diabetic neuropathy, diabetic
15 peripheral neuropathy, or neuropathy and ulcers resulting from said neuropathy as well as a manufacturing method for the latter, and use of nitric oxide.

With regard to nitric oxide (nitrogen monoxide, NO), its physiological and pharmacological roles have attracted
20 much attention and thus have been studied. NO is synthesized from arginine as the substrate by nitric oxide synthase (NOS). NOS is classified into a constitutive enzyme, cNOS, which is present even in the normal state of a living body and an inducible enzyme, iNOS, which is
25 produced in a large amount in response to a certain stimulus. It is known that, as compared with the concentration of NO produced by cNOS, the concentration of NO produced by iNOS is 2 to 3 orders higher, and that iNOS produces an extremely large amount of NO.

30 In the case of the generation of a large amount of NO as in the case of the production by iNOS, it is known that NO reacts with active oxygen to attack exogenous microorganisms and cancer cells, but also to cause inflammation and tissue injury. On the other hand, in the

case of the generation of a small amount of NO as in the case of the production by cNOS, it is considered that NO takes charge of various protective actions for a living body through cyclic GMP (cGMP), such as vasodilator action, improvement of the blood circulation, antiplatelet-aggregating action, antibacterial action, anticancer action, acceleration of the absorption at the digestive tract, renal function regulation, neurotransmitting action, erection (reproduction), learning, appetite, and the like. Heretofore, inhibitors of the enzymatic activity of NOS have been examined for the purpose of preventing inflammation and tissue injury, which are considered to be attributable to NO generated in a large amount in a living body. However, the promotion of the enzymatic activity (or expressed amount) of NOS (in particular, cNOS) has not been examined for the purpose of exhibiting various protective actions for a living body by promoting the enzymatic activity of NOS and producing NO appropriately.

In recent years research has been directed to polymers with the capability of releasing nitrogen oxide when getting in contact with water. Such polymers are for example polyalkyleneimines, such as L-PEI (Linear PolyEthyleneImine) and B-PEI (Branched PolyEthyleneImine), which polymers have the advantage of being biocompatible, after the release of nitrogen oxide.

The polymers employed in embodiments of the present invention may be manufactured by electro spinning, gas spinning, air spinning, wet spinning, dry spinning, melt spinning, and gel spinning. Electro spinning is a process by which a suspended polymer is charged. At a characteristic voltage a fine jet of polymer releases from the surface in response to the tensile forces generated by interaction by an applied electric field with the electrical charge carried by the jet. This process produces a bundle of polymer fibres, such as nano-fibres. This jet

of polymer fibres may be directed to a surface to be treated.

Furthermore, US 6,382,526, US 6,520,425, and US 6,695,992 disclose processes and apparatuses for the production of such polymeric fibres. These techniques are generally based on gas stream spinning, also known within the fiber forming industry as air spinning, of liquids and/or solutions capable of forming fibers. Gas stream spinning is suited for producing devices according to certain embodiments of the invention.

In an embodiment of the invention, according to Fig. 1B, the device is in form of sock 12, manufactured of a combination of L-PEI or other NO-eluting polymer, such as amino cellulose, amino dextrans, chitosan, aminated chitosan, polyethyleneimine, PEI-cellulose, polypropyleneimine, polybutyleneimine, polyurethane, poly(buthanediol spermate), poly(iminocarbonate), polypeptide, Carboxy Methyl Cellulose (CMC), polystyrene, poly(vinyl chloride), and polydimethylsiloxane, or any combinations of these, and these mentioned polymers grafted to an inert backbone, such as a polysaccharide backbone or cellulosic backbone, and other suitable carrier materials, such as polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, and latex, or any combinations of these, as base material, said sock being expandable, where NO is allowed to be eluted, said sock being covered on the inside with nano-filament of NO-eluting L-PEI. The base material of the sock may also be cotton, polyacrylate or any other fabric used in the clothing industry, in which cases the base material is

loaded with the NO-eluting polymer according to the invention. This embodiment provides an easy to use sock, which is applied on the affected area in the same way as normal clothing. In another embodiment of the present
5 invention the sock is covered on the inside with nano-filament of any other suitable polymer, according to above. Such polymers are for example other polyalkyleneimines, such as B-PEI (Branched PolyEthyleneImine), which polymers have the advantage of being biocompatible, after the
10 release of nitrogen oxide.

Other example for NO eluting polymers are given in US-5,770,645, wherein polymers derivatized with at least one -NOX group per 1200 atomic mass unit of the polymer are disclosed, X being one or two. One example is an S-
15 nitrosylated polymer and is prepared by reacting a polythiolated polymer with a nitrosylating agent under conditions suitable for nitrosylating free thiol groups.

Akron University has developed NO-eluting L-PEI molecule that can be nano-spun onto the surface of
20 permanently implanted medical devices such as implanted grafts, showing significant improvement of the healing process and reduced inflammation when implanting such devices. According to US-6,737,447, a coating for medical devices provides nitric oxide delivery using nanofibers of
25 linear poly(ethylenimine)-diazoniumdiolate. Linear poly(ethylenimine)diazoniumdiolate releases nitric oxide (NO) in a controlled manner.

However, the meaning of "controlled" in the context of US 6,737,447 is only directed to the fact that nitric
30 oxide is eluted from the coating during a period of time, i.e that the nitric oxide not is eluted all in once. Therefore, the interpretation of "controlled" in respect of US 6,737,447 is different from the meaning of "regulating" in the present invention. "Regulate or control", according
35 to the present invention is intended to be interpreted as

the possibility to vary the elution of nitric oxide to thereby achieve different elution profiles.

A polymer comprising an O-nitrosylated group is also a possible nitric oxide eluting polymer. Thus, in one
5 embodiment of the present invention, the nitric oxide eluting polymer comprises diazeniumdiolate groups, S-nitrosylated and O-nitrosylated groups, or any combinations thereof.

In still another embodiment of the present invention
10 said nitric oxide eluting polymer is a poly(alkyleneimine)diazeniumdiolate, such as L-PEI-NO (linear poly(ethyleneimine)diazeniumdiolate), where said nitric oxide eluting polymer is loaded with nitric oxide through the diazeniumdiolate groups and arranged to release
15 nitric oxide at a treatment site.

Some other examples of a suitable nitric oxide eluting polymer are selected from the group comprising mino cellulose, amino dextrans, chitosan, aminated chitosan, polyethyleneimine, PEI-cellulose, polypropyleneimine,
20 polybutyleneimine, polyurethane, poly(buthanediol spermate), poly(iminocarbonate), polypeptide, Carboxy Methyl Cellulose (CMC), polystyrene, poly(vinyl chloride), and polydimethylsiloxane, or any combinations of these, and these mentioned polymers grafted to an inert backbone, such
25 as a polysaccharide backbone or cellulosic backbone.

In still another embodiment of the present invention the nitric oxide eluting polymer may be a O-derivatized NONOate. This kind of polymer often needs an enzymatic reaction to release nitric oxide.

30 Other ways of describing polymers, which may be suitable as nitric oxide eluting polymer, is polymers comprising secondary amine groups (=N-H), such as L-PEI, or have a secondary amine (=N-H) as a pendant, such as aminocellulose.

It is most preferable that the nano-spun fibres in the NO-eluting sock according to the present embodiment of the present invention comprise L-PEI. Also, nitric oxide eluting fibers to be woven into the sock are suitably
5 produced from L-PEI and loaded with NO for release thereof at use.

The term "nano-spun fibers" is in the context of the present invention intended to be interpreted as fibers obtained all processes producing fibers of nano-size, such
10 as electro spinning, air spinning, wet spinning, dry spinning, melt spinning, gel spinning.

This sock may be in any suitable size, such as a suitable size for covering any body part to be treated, such as a foot or individual toes, a calf, a thigh, the
15 whole or a part of an abdomen, a neck, the whole or a part of a head, a shoulder, an upper arm, a forearm, a hand or individual fingers. These sizes may for example vary from small, medium, and large sized socks, depending on the size of the person to be treated.

20 When the NO-eluting sock 12 according to the present embodiment of the invention is applied on the area to be treated, according to Fig. 1B, and gets in contact with the moisture, in form of secreted sweat, or sprayed proton donor, the NO-eluting sock starts to release NO to the area
25 to be treated.

In another embodiment of the present invention the sock is covered on the inside with NO-eluting nano-particles, or micro-spheres. These nano-particles, or micro-spheres, may be formed from the NO-eluting polymers, encapsulated in any suitable material, such as
30 polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene,
35 polyethers, polycarbonates, polyamides, poly(acrylic acid),

Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, and latex, or any combinations of these. When the nano-particles, or micro-spheres, according to this embodiment, gets in contact with
5 the secreted moisture, in form of sweat, or sprayed proton donor, on the inside of the sock, they start to elute NO on the area to be treated.

In the context of the present invention the term "encapsulating" is intended to be interpreted as fixating
10 the nitric oxide eluting polymer in a three dimensional matrix such as a foam, a film, a nonwoven mat of nano-fibers, fibers, or other materials with the capability to fixate the NO eluting polymer, or enclosing the nitric oxide eluting polymer in any suitable material.

15 In yet another embodiment of the present invention the sock contains a small water bag or sealed water sponge. This water bag or sealed water sponge is used to activate the elution of NO from the NO-eluting polymer, nano-particles, and/or micro-spheres. Persons that do not easily
20 sweat may be helped by the use of this embodiment.

In another embodiment of the present invention a nitric oxide eluting polymer is provided, and/or combined, with microencapsulated proton donor.

This may for example be done by first manufacture
25 micro capsules, containing a proton donor, such as water or water containing liquid, in a state of the art manner. These micro capsules are then applied on the NO eluting polymer. The application of the micro capsules on the NO eluting polymer may for example be done by gluing, such as
30 pattern gluing, or instead spinning the NO eluting polymer onto said micro capsules. In this way a device or a system, comprising NO eluting polymer and micro encapsulated proton donor is manufactured. When the device or system is applied on the target area the device or system is compressed or
35 squeezed. Said compression or squeezing results in breakage

of the micro capsules. The NO eluting polymer is thus exposed to proton donor, and the elution of NO from the NO eluting polymer is initiated on the target area. In other embodiments of the present invention the proton donor
5 inside the micro capsules is released by heating or shearing the micro capsules until the micro capsules are ruptured.

In still another embodiment the micro capsules are formed into a film, tape, or sheath. Thereafter, a film,
10 tape, or sheath of an NO eluting polymer is glued onto the film, tape, or sheath of micro capsules. Preferably the film, tape, or sheath of the NO eluting polymer is glued onto the film, tape, or sheath of the micro capsules in patterned way. The obtained pattern includes spaces where
15 there is no glue, in which spaces the proton donor will be transported to the NO eluting polymer once the micro capsules are broken from compression or squeezing. When the proton donor gets in contact with the NO eluting polymer the elution of NO starts. Thus, the combination of film,
20 tape, or sheath of micro capsules and NO eluting polymer may be applied on a target area. Thereafter the combination is compressed or squeezed, which results in that the target area is exposed to NO.

I yet another embodiment the NO eluting polymer is
25 spun directly onto the film, tape, or sheath of micro capsules, containing proton donor. The combination of film, tape, or sheath of micro capsules and spun NO eluting polymer may be applied on a target area. Thereafter the combination is compressed or squeezed, which results in
30 that the target area is exposed to NO.

In still another embodiment of the present invention the device or system is provided with an activation indicator. This activation indicator indicates when the micro capsules are satisfyingly broken, hence when the NO
35 eluting polymer is subjected to enough proton donor to

elute an efficient amount of NO. This activation indicator may for example be obtained by colouring the proton donor that is trapped inside the micro capsules. When the micro capsules are broken the coloured proton donor escapes the microcapsules and the colour gets visualised while efficiently wetting the NO eluting polymer. Another way of obtaining an activation indicator is to choose to manufacture the micro capsules in a material, or choose a wall thickness of said micro particles, that creates a sound when the micro capsules break. It is also possible to admix a scent in the proton donor, contained in the micro capsules. This results in that the user of the device or system may smell the scent when the proton donor escapes from the micro capsules after breakage thereof.

15 In another embodiment a substance that changes color when it comes in contact with water can be incorporated in the device. Thus when the water capsules or water bag breaks the material changes color, thereby indicating that the material is activated.

20 In another embodiment of the present invention the device or system only allows NO-elution in one direction. In this kind of embodiment one side of the device has low permeability, or substantially no permeability, to nitric oxide. This may also be accomplished by applying a material on one side of the device according to the invention that is not permeable to NO. Such materials may be chosen from the group comprising common plastics, such as fluoropolymers, polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, 25 polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, 30 and latex, or any combinations of these. This embodiment is

also easy to manufacture as the NO eluting polymer, e.g. L-PEI (or nitric oxide eluting polymer and carrier material, which will be explained in more detail below) may be electro or gas-jet spun onto the surface of the device
5 according to the invention of e.g. the mentioned plastics, latex, or cotton.

In still another embodiment the device is provided with one membrane, which is permeable to nitric oxide, on a first side of the device, and another membrane, which has
10 low permeability or substantially no permeability to nitric oxide, on a second side of said device. This embodiment provides the possibility to direct the elution to said first side of the device, while the elution of nitric oxide is substantially prevented from said second side. Thereby,
15 a greater amount of nitric oxide will reach the intended area to be treated.

The activation of the nitric oxide eluting polymer may be accomplished by contacting said polymer with a suitable proton donor. In one embodiment the proton donor
20 may be selected from the group comprising water, body fluids (blood, lymph, bile, etc.), alcohols (methanol, ethanol, propanols, butanols, pentanols, hexanols, phenols, naphthols, polyols, etc.), aqueous acidic buffers (phosphates, succinates, carbonates, acetates, formates,
25 propionates, butyrates, fatty acids, amino acids, etc.), or any combinations of these.

By adding a surfactant in the proton donor one can facilitate the wetting of the device. The surfactant lowers the surface tension and the activating fluid is
30 easily transported throughout the device.

In still another embodiment of the device according to the present invention, it may be manufactured in the form of a polyurethane, or polyethylene, tape or coating, according to Fig. 2. This polyurethane tape or coating may
35 easily be wrapped around the body part to be treated. At

least the side facing the body part may be covered with NO-eluting nano-particles, micro-spheres, or nano-filament of NO-eluting L-PEI. When these particles or filaments get in contact with the moisture, in form of sweat, on the inside
5 of the tape or coating, the elution of NO starts.

This embodiment makes it possible to obtain a device that may be applied on locations that are difficult to get at with a sock, such as in between the toes or fingers, the groin, the armpit etc.

10 In other embodiments of the invention, the tape or coating may be manufactured by any other suitable material, such as rubbers and polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates,
15 polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, and latex, or any combinations of these.

20 In another embodiment these nano-particles, or micro-spheres, may be integrated in a soluble film that disintegrates on the inside of the sock or tape/coating, in order to elute NO at the area of interest when the soluble film gets in contact with the moisture, in form of sweat or
25 from the water bag or sealed water sponge, or spraying water on the area to be treated.

When placed on an area to be treated the device provides target treatment and/or prevention of neuropathy, such as diabetic neuropathy, diabetic ulcers, and macro-
30 angiopathy.

In another embodiment of the present invention the device only allows NO-elution in one direction. In this kind of embodiment one side of the sock or tape/coating is non-permeable to NO. This may be accomplished by applying a
35 material on one side of the sock or tape/coating that is

not permeable to NO. Such materials may be chosen from the group comprising common plastics, such as polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, and latex, or any combinations of these.

10 In another embodiment of the present invention, the device is in form of polyurethane or polyethylene sheaths or plasters, pads or dressings according to Fig. 3, coated with the NO-eluting polymer. The plaster or sheath may be applied on the area to be treated with the aid of an
15 adhering material, such as glue etc. This embodiment has the advantage of being applicable on smaller areas or wounds, when there is no need, or if the person to be treated finds it unpleasant, to cover the whole body part with a sock or coating/tape. It is also an advantage that
20 the device in form of a plaster or sheath or pad or dressing needs lesser amount of material, thus lower manufacturing cost.

The devices according to the embodiments may also be covered with a powder manufactured from nano-fibres of NO-eluting polymer, such as L-PEI.

In yet another embodiment of the present invention the NO-eluting device is acting as a booster for drug eluting patches, e.g. pharmaceuticals, vitamins, nicotin, nitroglycerin etc. This embodiment presents a device with
30 the advantage of combining two therapeutic treatments, of significant value, in one treatment. Hence, a synergetic effect may be achieved by such devices when NO that is eluted from the device. NO has a vasodilatory effect on the region where the device having the combination compound
35 actuates. Vasodilated tissue is more susceptible to certain

medications and thus more easily treated by the medical preparations and still NO has in addition to that the anti-inflammatory, anti-bacterial etc. effect. Hence, an unexpected surprisingly effective treatment is provided.

5 In another embodiment of the device according to the present invention the fibres, nano-particles, or micro-spheres may be integrated in a gel, that may either be in a smearing or compressed structure. The elution of NO may then be initiated by applying a water soaked patch on said
10 gel. The fibres, nano-particles, or micro-spheres may also be integrated in a hydrogel, which is mixed directly before use. This embodiment has the advantage of being able to penetrate pockets and corners in the skin for closer elution of NO on the area to be treated.

15 In still another embodiment the nitric oxide eluting polymer, such as powder, nano-particles or micro-spheres, can be incorporated in foam. The foam may have an open cell structure, which facilitates the transport of the proton donor to the nitric oxide eluting polymer. The foam can be
20 of any suitable polymer such as polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates,
25 polyamides, poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, polyolefins, and latex, or any combinations of these, or latex.

In another embodiment the device is in form of a
30 cream, a gel or a combination of the two. Since the nitric oxide eluting polymer is activated by proton donors the nitric oxide eluting polymer has to be separate from the proton donor until one wants to initiate the elution of nitric oxide, i.e. use the device. One way to accomplish
35 this is to have a syringe with two separate containers. In

one container you have a proton donor-based gel and in the other a non proton donor-based gel, comprising the nitric oxide eluting polymer. Upon using the device the two gels are squeezed from the syringe and mixed together, the
5 proton donor in the first gel comes in contact with the nitric oxide eluting polymer in the second gel and the elution of nitric oxide starts.

The device elutes nitric oxide (NO) from said eluting polymer in a therapeutic dose, such as between 0.001 to
10 5000 ppm, such as 0.01 to 3000 ppm, such as 0.1 to 1000 ppm, such as 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 32, 33, 34, 35, 36, 37, 38, 39, 40, 41, 42, 43, 44, 45, 46, 47, 48, 49, 50, 51, 52, 53, 54, 55, 56, 57, 58, 59,
15 60, 61, 62, 63, 64, 65, 66, 67, 68, 69, 70, 71, 72, 73, 74, 75, 76, 77, 78, 79, 80, 81, 82, 83, 84, 85, 86, 87, 88, 89, 90 91, 92, 93, 94, 95, 96, 97, 98, 99, or 100 ppm. The concentration may vary widely depending on where the concentration is measured. If the concentration is measured
20 close to the actual NO eluting polymer the concentration may be as high as thousands of ppm, while the concentration inside the tissue in this case often is considerably lower, such as between 1 to 1000 ppm.

In the embodiments of the present invention it may be
25 suitable to control or regulate the time span of NO release from the device according to the invention. This may be accomplished by integrating other polymers or materials in said device. These polymers or materials may be chosen from any suitable material or polymer, such as polyethylene,
30 polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose
35 (CMC), protein based polymers, gelatine, biodegradable

polymers, cotton, polyolefins, and latex, or any combinations of these, or latex.

Three important factors in controlling and regulating the elution of nitric oxide from a nitric oxide eluting polymer are how quickly a proton donor comes in contact with the nitric oxide releasing polymer, such as a diazolumdiolate group, the acidity of the environment surrounding the nitric oxide eluting polymer, and the temperature of the environment surrounding the nitric oxide releasing polymer (higher temperature promotes elution of nitric oxide).

In one embodiment of the present invention a nitric oxide eluting polymer, such as L-PEI-NO, is mixed with a carrier polymer to slow down or prolong the elution of nitric oxide. Also, in another embodiment, the nitric oxide eluting polymer may be mixed with more than one carrier polymer, whereby the elution or release may be tailor made to fit specific needs. Such a need may for example be a low elution during a first period of time, when the environment of the nitric oxide eluting polymer is hydrophobic, and a faster elution during a second period of time, when the environment of the nitric oxide eluting polymer has been altered to be more hydrophilic. This may for example be accomplished by using biodegradable polymers, whereby a low elution during a first period of time is obtained, after which, when the hydrophobic polymer has been dissolved, the hydrophilic polymer provides a higher elution of nitric oxide. Thus, a more hydrophobic carrier polymer will give a slower elution of nitric oxide, since the activating proton donor, such as water or body fluid, will penetrate the carrier polymer slower. On the other hand, a hydrophilic polymer acts the opposite way. One example of an hydrophilic polymer is polyethylene oxide, and one example of an hydrophobic polymer is polystyrene. These carrier polymers may be mixed with the nitric oxide eluting polymer

and then electrospun to suitable fibers. The skilled person in the art knows which other polymers may be used for similar purposes. Fig. 4 illustrates two elution profiles (NO concentration vs. time) for two different polymer mixtures; a nitric oxide eluting polymer mixed with a hydrophilic carrier polymer in an acidic environment (A), and a nitric oxide eluting polymer mixed with a hydrophobic carrier polymer in a neutral environment (B).

In one embodiment this carrier polymer is substituted by another material with hydrophobic or hydrophilic properties. Therefore, the term "carrier material" in the present context should be interpreted to include carrier polymers and other materials with hydrophilic or hydrophobic properties.

In another embodiment of the present invention the elution of nitric oxide from a nitric oxide eluting polymer, such as L-PEI-NO, is influenced by the presence of protons. This means that a more acidic environment provides a quicker elution of nitric oxide. By activating the nitric oxide eluting polymer, or mixture of nitric oxide eluting polymer and carrier material, with an acidic fluid, such as an ascorbic acid solution, the elution of nitric oxide may be accelerated.

The carrier polymers and carrier materials mentioned above may affect other characteristics than the regulation of nitric oxide elution. An examples of such characteristic is mechanical strength.

In respect of the carrier polymers or carrier materials, the NO-eluting polymer may be integrated in, spun together with, or spun on top of, any of these materials in all of the embodiments of the present invention. This spinning includes electro spinning, air spinning, dry spinning, wet spinning, melt spinning, and gel spinning. In this way, one may manufacture fibers of a polymer mixture, comprising a nitric oxide eluting polymer

and a carrier polymer, or a carrier material, with predefined nitric oxide eluting characteristics. These characteristics may be tailor made for different elution profiles in different applications.

5 The NO-eluting polymers in the devices may be combined with silver, such as hydroactivated silver. The integration of silver in the devices gives the healing process an extra boost. Preferably the silver is releasable from the devices in the form of silver ions. The
10 integration of silver in the device may present several advantages. One example of such an advantage is that the silver may keep the device in itself free from bacteria or viruses, while the nitric oxide eluting polymer elutes the therapeutic dosage of nitric oxide to the target site.

15 The device may be manufactured by, for example electro spinning of L-PEI. L-PEI is the charged at a characteristic voltage, and a fine jet of L-PEI releases as a bundle of L-PEI polymer fibres. This jet of polymer fibres may be directed to a surface to be treated. The
20 surface to be treated may for example be any suitable material in respect of a device. The electro spun fibres of L-PEI then attach on said material and form a coating/layer of L-PEI on the device according to the invention.

 The basic material of the device may be polyethylene,
25 polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose
30 (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, polyolefins, and latex, or any combinations of these, or latex. The NO-eluting polymer may be integrated in, spun together with, or spun on top of, any of these materials in all of the embodiments of the
35 present invention.

The nitric oxide eluting polymer may comprise a secondary amine, either in the backbone or as a pendant, as described previously. This will make a good nitric oxide eluting polymer. The secondary amine should have a strong
5 negative charge to be easy to load with nitric oxide. If there is a ligand close to the secondary amine, such as on a neighbour carbon atom to the nitrogen atom, with higher electronegativity than nitrogen (N), it is very difficult to load the polymer with nitric oxide. On the other hand,
10 if there is a positive ligand close to the secondary amine, such as on a neighbour carbon atom to the nitrogen atom, the electronegativity of the amine will increase and thereby increase the possibility to load the nitric oxide elution polymer with nitric oxide.

15 In an embodiment of the present invention the nitric oxide polymer may be stabilized with a salt. Since the nitric oxide eluting group, such as a diazeniumdiolate group, is negative, a positive counter ion, such as a cation, may be used to stabilize the nitric oxide eluting
20 group. This cation may for example be selected from the group comprising any cation from group 1 or group 2 in the periodic table, such as Na^+ , K^+ , Li^+ , Be^{2+} , Ca^{2+} , Mg^{2+} , Ba^{2+} , and/or Sr^{2+} . Different salts of the same nitric oxide eluting polymer have different properties. In this way a
25 suitable salt (or cation) may be selected for different purposes. Examples of cationic stabilized polymers are L-PEI-NO-Na, i.e. L-PEI diazeniumdiolate stabilized with sodium, and L-PEI-NO-Ca, i.e. L-PEI diazeniumdiolate stabilized with calcium.

30 Another embodiment of the present invention comprises mixing the nitric oxide eluting polymer, or a mixture of the nitric oxide eluting polymer and a carrier material, with an absorbent agent. This embodiment provides the advantage of an accelerated elution of nitric oxide since
35 the polymer, or polymer mixture, via the absorbent agent,

may take up the activating fluid, such as water or body fluid, much faster. In one example 80 % (w/w) absorbent agent is mixed with the nitric oxide eluting polymer, or mixture of nitric oxide eluting polymer and carrier material, and in another embodiment 10 to 50 % (w/w) absorbent agent is mixed with the nitric oxide eluting polymer, or mixture of nitric oxide eluting polymer and carrier material.

Since the elution of nitric oxide is activated by a proton donor, such as water, it may be an advantage to keep the nitric oxide eluting polymer, or mixture of nitric oxide eluting polymer and carrier material, in contact with said proton donor. If an indication requires an elution of nitric oxide during a prolonged period of time, a system is advantageous, which presents the possibility to keep the proton donor in contact with the nitric oxide eluting polymer, or mixture of nitric oxide eluting polymer and carrier material. Therefore, in still another embodiment of the present invention, the elution of nitric oxide may be regulated by adding an absorbent agent. The absorbent agent absorbs the proton donor, such as water, and keeps the proton donor in close contact with the nitric oxide eluting polymer during prolonged periods of time. Said absorbent agent may be selected from the group comprising polyacrylates, polyethylene oxide, carboxymethylcellulose, and microcrystalline cellulose, cotton, and starch. This absorbent agent may also be used as a filling agent. In this case said filling agent may give the nitric oxide eluting polymer, or mixture of said nitric oxide eluting polymer and a carrier material, a desired texture.

It is of course possible to electro spin the other NO-eluting polymers, according to above, on the device according to the invention while still being inside the scope of the present invention.

In one embodiment the NO-eluting polymers employed in the devices according to the present invention are electro spun in such way that pure NO-eluting polymer fibres may be obtained.

5 Gas stream spinning, air spinning, wet spinning, dry spinning, melt spinning, or gel spinning of said NO-eluting polymers onto the device is also within the scope of the present invention.

The manufacturing process presents the advantages of
10 large contact surface of the NO-eluting polymer fibres or micro particles with the area to be treated, effective use of NO-eluting polymer, and a cost effective way of producing the device.

Hereinafter, some potential uses of the present
15 invention are described:

A method of therapeutically treating and/or preventing neuropathy and ulcers at a treatment side of a body, by means of a device that comprises a nitric oxide (NO) eluting polymer configured for eluting a therapeutic
20 dosage of nitrogen oxide (NO) when used for said treatment, comprising exposing said treatment site of said infection in or on a body to said nitric oxide when said polymer in use elutes nitrogen oxide (NO) by eluting a therapeutic dose of nitric oxide from said nitric oxide eluting polymer
25 to said treatment site.

The method according to the above, wherein said site is an extremity of a body, and wherein said method comprises applying a condom/sheath, sock, patch/pad/dressing, and tape/coating to said extremity for
30 said exposure.

Use of nitric oxide (NO) in a therapeutic dose for therapeutically treating and/or preventing neuropathy and ulcers at a treatment side of a body.

The invention may be implemented in any suitable
35 form. The elements and components of the embodiments

according to the invention may be physically, functionally, and logically implemented in any suitable way. Indeed, the functionality may be implemented in a single unit, in a plurality of units, or as part of other functional units.

5 Although the present invention has been described above with reference to specific embodiments, it is not intended to be limited to the specific form set forth herein. Rather, the invention is limited only by the accompanying claims and, other embodiments than the
10 specific above are equally possible within the scope of these appended claims.

 In the claims, the term "comprises/comprising" does not exclude the presence of other elements or steps. Furthermore, although individually listed, a plurality of
15 means, elements or method steps may be implemented. Additionally, although individual features may be included in different claims, these may possibly advantageously be combined, and the inclusion in different claims does not imply that a combination of features is not feasible and/or
20 advantageous. In addition, singular references do not exclude a plurality. The terms "a", "an", "first", "second" etc do not preclude a plurality. Reference signs in the claims are provided merely as a clarifying example and shall not be construed as limiting the scope of the claims
25 in any way.

CLAIMS

1. A device configured to therapeutically target
treat and/or prevent neuropathy, or neuropathy and ulcers
5 resulting from said neuropathy, at a target side of a body,
wherein

said device comprises a nitric oxide (NO) eluting
polymer configured to elute a therapeutic dosage of nitric
oxide (NO) when used for said treatment and/or prevention,
10 and wherein said device is configured to expose said target
site in or on a body to said nitric oxide when said polymer
in use elutes nitric oxide (NO),

c h a r a c t e r i z e d in that

said nitric oxide (NO) eluting polymer is integrated
15 with a carrier material, such that said carrier material,
in use, regulates and controls the elution of said
therapeutic dosage of nitric oxide (NO).

2. Device according to claim 1, wherein said nitric
20 oxide (NO) eluting polymer comprises diazeniumdiolate
groups, S-nitrosylated groups, and O-nitrosylated groups,
or any combination these.

3. Device according to claim 1 or 2, wherein said
25 nitric oxide (NO) eluting polymer is L-PEI (linear
polyethyleneimine), loaded with nitric oxide (NO) through
said diazeniumdiolate groups, S-nitrosylated groups, or O-
nitrosylated groups, or any combination these, arranged for
release of the nitric oxide (NO) at said target site in or
30 on a body for treatment of or prevention of neuropathy at
the site.

4. Device according to claim 1, wherein said nitric
oxide eluting polymer is selected from the group comprising
35 mino cellulose, amino dextrans, chitosan, aminated
chitosan, polyethyleneimine, PEI-cellulose,

polypropyleneimine, polybutyleneimine, polyurethane, poly(buthanediol spermate), poly(iminocarbonate), polypeptide, Carboxy Methyl Cellulose (CMC), polystyrene, poly(vinyl chloride), and polydimethylsiloxane, or any
5 combinations of these, and these mentioned polymers grafted to an inert backbone, such as a polysaccharide backbone or cellulosic backbone.

5. Device according to claim 1, wherein said device
10 has a form selected from the group consisting of a sock, a tape/coating, a patch or dressing and a plaster, configured to therapeutically target treat and/or prevent diabetic neuropathy, macro-angiopathy, diabetic ulcers, and/or vaso-
constrictive disorders at said treatment site.

15

6. Device according to claim 5, wherein said sock, tape/coating, or plaster is manufactured from polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose,
20 polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides, poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein based polymers, gelatine, biodegradable polymers, cotton, polyolefins, and latex, or any
25 combinations of these,, and said sock, tape/coating, or a plaster includes said nitric oxide (NO) eluting polymer configured for in use eluting said nitric oxide (NO) to said target site.

30 7. Device according to any of claims 1 to 6, including a proton donor bag, sealed proton donor sponge, or microencapsulated proton donor.

8. Device according to claim 1 to 7, wherein said device is partly disintegrable when subjected to a proton donor.

5 9. Device according to claim 7 or 8, wherein said proton donor is selected from the group comprising water, blood, lymph, bile, methanol, ethanol, propanols, buthanols, pentanols, hexanols, phenols, naphtols, polyols, phosphates, succinates, carbonates, acetates, formats,
10 propionates, butyrates, fatty acids, and amino acids, or any combinations of these.

 10. Device according to claim 9, said proton donor having added a surfactant thereto, said surfactant in use
15 facilitating wettening of the device.

 11. Device according to claim 1, wherein said polymer comprises silver, configured to expose said target site.

20 12. Device according to claim 1, wherein said polymer is configured to act as a booster for drug eluting patches when used.

 13. Device according to claim 1, wherein said nitric
25 oxide eluting polymer is in form of nano-particles or micro-spheres.

 14. Device according to claim 13, wherein said nano-particles, or micro-spheres, are encapsulated in suitable
30 material, such as polyethylene, polypropylene, polyacrylonitrile, polyurethane, polyvinylacetates, polylacticacids, starch, cellulose, polyhydroxyalkanoates, polyesters, polycaprolactone, polyvinylalcohol, polystyrene, polyethers, polycarbonates, polyamides,
35 poly(acrylic acid), Carboxy Methyl Cellulose (CMC), protein

based polymers, gelatine, biodegradable polymers, cotton, polyolefins, and latex, or any combinations of these..

15. Device according to claim 13, wherein said nano-
5 particles, or micro-spheres, are integrated in a gel, hydrogel, foam or cream.

16. Device according to claim 1, wherein said carrier
material is selected from the group consisting of
10 polyethylene, polypropylene, polyacrylonitrile,
polyurethane, polyvinylacetates, polylacticacids, starch,
cellulose, polyhydroxyalkanoates, polyesters,
polycaprolactone, polyvinylalcohol, polystyrene,
polyethers, polycarbonates, polyamides, poly(acrylic acid),
15 Carboxy Methyl Cellulose (CMC), protein based polymers,
gelatine, biodegradable polymers, cotton, polyolefins, and
latex, or any combinations of these.

17. Device according to claim 1, wherein said nitric
20 oxide eluting polymer comprises a secondary amine in the
backbone or a secondary amine as a pendant.

18. Device according to claim 17, wherein a positive
ligand is located on a neighbour atom to the secondary
25 amine.

19. Device according to claim 1 or 16, comprising an
absorbent agent.

20. Device according to claim 19, wherein said
30 absorbent agent is selected from the group comprising
polyacrylate, polyethylene oxide, Carboxy Methyl Cellulose
(CMC), microcrystalline cellulose, cotton, or starch, or
any combinations thereof.

21. Device according to claim 1, 16, 17 or 18, comprising a cation, said cation stabilizing the nitric oxide eluting polymer.

5 22. Device according to claim 21, wherein said cation is selected from the group comprising Na^+ , K^+ , Li^+ , Be^{2+} , Ca^{2+} , Mg^{2+} , Ba^{2+} , and/or Sr^{2+} , or any combinations thereof.

10 23. Device according to claim 1, wherein said carrier material is a hydrogel.

15 24. Device according to claim 1, wherein the nitric oxide eluting polymer is activateable by proton donors, wherein a the nitric oxide eluting polymer is, prior to use, stored separate from the proton donor until initiation of elution of nitric oxide therefrom.

20 25. Device according to claim 24, wherein the device is a syringe-type device having two separate containers, wherein a first container contains a proton donor-based NO release activation agent, such as a gel, and a second container contains a non proton donor-based gel, comprising the nitric oxide eluting polymer, wherein the syringe-type device is configured to provide admixing upon
25 administration to said target site.

30 26. A manufacturing process for a device configured to therapeutically target treat and/or prevent neuropathy, or neuropathy and ulcers resulting from said neuropathy, at a target side of a body, according to claim 1, comprising:
 selecting a nitric oxide (NO) eluting polymer configured to elute a therapeutic dosage of nitric oxide (NO) when used for said therapeutic treatment and/or prevention of neuropathy, or neuropathy and ulcers
35 resulting from said neuropathy,

selecting a carrier material, which carrier material is configured to regulate and control the elution of said therapeutic dosage of nitric oxide (NO),

incorporating the NO-eluting polymer with said
5 carrier material into an nitric oxide (NO) eluting material, such that said carrier material, in use of said device, regulates and controls the elution of said therapeutic dosage of nitric oxide (NO), and

deploying said nitric oxide eluting material into a
10 suitable form, or as a coating onto a carrier, to form at least a part of said device, such that said device is configured to expose a therapeutic target site to said nitric oxide when said NO-eluting polymer in use elutes nitric oxide (NO).

15

27. The manufacturing process according to claim 26, wherein said deploying comprises electro spinning, air spinning, gas spinning, wet spinning, dry spinning, melt spinning, or gel spinning of NO-eluting polymer.

20

28. The manufacturing process according to claim 26 or 27, wherein said selecting said nitric oxide (NO) eluting polymer comprises selecting a plurality of nitric oxide (NO) eluting polymeric particles, preferably nano
25 fibres, nano particles or micro spheres.

29. The manufacturing process according to claim 26 or 27, wherein said incorporating said NO-eluting polymer with said carrier material comprises integrating said NO-
30 eluting polymer in said carrier material, spinning said NO-eluting polymer together with said carrier material, or spinning said NO-eluting polymer on top of said carrier material, in order to predefine nitric oxide eluting characteristics of said device.

35

30. The manufacturing process according to claim 26, further comprising integrating silver in said device.

31. The manufacturing process according to claim 26,
5 further comprising microencapsulating proton donor in micro capsules, and
applying the micro capsules to said nitric oxide (NO) eluting material.

10 32. The manufacturing process according to claim 31, wherein said applying comprises pattern gluing, or spinning the NO eluting material onto said micro capsules.

33. The manufacturing process according to claim 31,
15 comprising forming the micro capsules into a first film, tape, or sheath,
forming a second film, tape, or sheath of said NO eluting material, and
gluing the first film, tape, or sheath of micro
20 capsules to said second film, tape, or sheath of said NO eluting material.

34. The manufacturing process according to claim 33, wherein said gluing comprises patterned gluing, such that a
25 pattern is obtained including glue free spaces.

35. The manufacturing process according to claim 31, comprising forming the micro capsules into a first film, tape, or sheath, and directly spinning the NO eluting
30 material onto the film, tape, or sheath of micro capsules, containing a proton donor.

36. The manufacturing process according to claim 31, comprising providing an activation indicator configured to
35 indicate when the micro capsules are broken such that the

NO eluting material is subjected to said proton donor to elute NO.

37. The manufacturing process according to claim 36,
5 wherein said providing an activation indicator comprises providing a coloring agent inside the micro capsules.

38. The manufacturing process according to claim 36,
wherein said providing an activation indicator comprises
10 selecting a material for the micro capsules, or choosing a wall thickness of said micro capsules, that creates a sound when the micro capsules break.

39. The manufacturing process according to claim 36,
15 wherein said providing an activation indicator comprises admixing a scent material into the micro capsules.

40. The manufacturing process according to claim 36,
wherein said providing an activation indicator comprises
20 providing a substance that changes color when it comes in contact with the proton donor.

41. Use of a nitric oxide (NO) eluting polymer for the manufacture of a device for the treatment of
25 neuropathy, or neuropathy and ulcers resulting from said neuropathy, including diabetic peripheral neuropathy, wherein

nitric oxide that is loaded to said device is eluted as nitric oxide (NO) from said NO eluting polymer in a
30 therapeutic dose when used at a target side of a body.

42. Use according to claim 41, wherein said therapeutic dose is 0.001 to 5000 ppm, such as 0.01 to 3000 ppm, such as 0.1 to 1000 ppm, such as 1, 2, 3, 4, 5, 6, 7,
35 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22,

23, 24, 25, 26, 27, 28, 29, 30, 31, 32, 33, 34, 35, 36, 37,
38, 39, 40, 41, 42, 43, 44, 45, 46, 47, 48, 49, 50, 51, 52,
53, 54, 55, 56, 57, 58, 59, 60, 61, 62, 63, 64, 65, 66, 67,
68, 69, 70, 71, 72, 73, 74, 75, 76, 77, 78, 79, 80, 81, 82,
5 83, 84, 85, 86, 87, 88, 89, 90 91, 92, 93, 94, 95, 96, 97,
98, 99, or 100 ppm.

43. A method of therapeutically treating and/or
preventing neuropathy, or neuropathy and ulcers resulting
10 from said neuropathy, at a treatment side of a body, by
means of a device that comprises a nitric oxide (NO)
eluting polymer configured for eluting a therapeutic dosage
of nitrogen oxide (NO) when used for said treatment,
comprising
15 exposing said treatment site of said neuropathy in or
on a body to said nitric oxide when said polymer in use
elutes nitrogen oxide (NO) by eluting a therapeutic dose of
nitric oxide from said nitric oxide eluting polymer to said
treatment site.

20

44. The method according to claim 43, wherein said
site is an extremity of a body, and wherein said method
comprises applying a condom/sheath, sock,
patch/pad/dressing, and tape/coating to said extremity for
25 said exposure.

45. Use of nitric oxide (NO) in a therapeutic dose
for therapeutically treating and/or preventing neuropathy
and ulcers at a treatment side of a body.

30

46. Use of nitric oxide (NO) in a medicament for
therapeutically treating and/or preventing neuropathy and
ulcers at a treatment side of a body.

47. Use according to claim 45 or 46, wherein said neuropathy is diabetic peripheral neuropathy.

1/4




Fig. 1A




Fig. 1B

2/4




Fig. 2

3/4




Fig. 3

4/4




Fig. 4

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2006/050891

A. CLASSIFICATION OF SUBJECT MATTER

INV. A61L27/54 A61L29/16 A61K31/74 A61K31/785 A61L27/34
A61L29/08 A61L31/10 A61L31/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
A61L A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, EMBASE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2002/082221 A1 (HERRMANN ROBERT A ET AL) 27 June 2002 (2002-06-27) paragraph [0001] paragraph [0026] paragraph [0027] paragraph [0073] paragraph [0124]	1,2,5,6, 26,41,45
X	US 2002/094985 A1 (HERRMANN ROBERT A ET AL) 18 July 2002 (2002-07-18) paragraph [0026] paragraph [0058] - paragraph [0100] paragraph [0122] - paragraph [0125] ----- -/--	1-4,16, 26

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the International filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the International filing date but later than the priority date claimed

T later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

27 June 2006

Date of mailing of the International search report

11/07/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Staber, B

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2006/050891

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 110 453 A (KEEFER ET AL) 29 August 2000 (2000-08-29) column 3, line 22 - line 37 column 5, line 19 - line 24 column 8, line 28 - line 38 column 8, line 50 - line 58 -----	1-6, 13, 16
X	EP 1 300 424 A (MEDTRONIC AVE INC) 9 April 2003 (2003-04-09) paragraph [0018] paragraph [0022] paragraph [0034] paragraph [0039] -----	1-4, 10, 11, 13
X	US 5 691 423 A (SMITH ET AL) 25 November 1997 (1997-11-25) column 4, line 12 - line 21 column 8, line 26 - line 33 -----	1-5, 13, 16, 26
X	DATABASE EMBASE [Online] ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL; 2002, BOHL MASTERS K S ET AL: "Effects of nitric oxide releasing poly(vinyl alcohol) hydrogel dressings on dermal wound healing in diabetic mice" XP001206883 Database accession no. EMB-2002411411 abstract & WOUND REPAIR AND REGENERATION 2002 UNITED STATES, vol. 10, no. 5, 2002, pages 286-294, ISSN: 1067-1927 the whole document -----	1-5, 41, 45, 46
A	WO 03/078437 A (THE UNIVERSITY OF QUEENSLAND; SMITH, MAREE, THERESE; BROWN, LINDSAY; H) 25 September 2003 (2003-09-25) abstract -----	41-47
A	US 2004/068005 A1 (SZILVASSY ZOLTAN ET AL) 8 April 2004 (2004-04-08) abstract -----	41-47

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2006/050891

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2002082221	A1	27-06-2002	AU 2002246664 A1 30-07-2002
		CA 2443080 A1 25-07-2002	
		EP 1343485 A2 17-09-2003	
		JP 2004523520 T 05-08-2004	
		WO 02056874 A2 25-07-2002	
		US 2004259840 A1 23-12-2004	
US 2002094985	A1	18-07-2002	CA 2443895 A1 25-07-2002
		EP 1399134 A2 24-03-2004	
		JP 2005503834 T 10-02-2005	
		WO 02056864 A2 25-07-2002	
		US 2004171589 A1 02-09-2004	
US 6110453	A	29-08-2000	NONE
EP 1300424	A	09-04-2003	JP 2003201313 A 18-07-2003
		US 2005079148 A1 14-04-2005	
		US 2003077243 A1 24-04-2003	
US 5691423	A	25-11-1997	US 5525357 A 11-06-1996
		US 5718892 A 17-02-1998	
		US 5676963 A 14-10-1997	
		US 5405919 A 11-04-1995	
WO 03078437	A	25-09-2003	AU 2003209850 A1 29-09-2003
		CA 2479098 A1 25-09-2003	
		CN 1703416 A 30-11-2005	
		EP 1495026 A1 12-01-2005	
		JP 2005524676 T 18-08-2005	
US 2004068005	A1	08-04-2004	AU 7657101 A 30-01-2002
		CA 2415392 A1 24-01-2002	
		EP 1303304 A2 23-04-2003	
		HU 0002628 A2 29-06-2002	
		WO 0205795 A2 24-01-2002	
		JP 2004503585 T 05-02-2004	